

Material datasheet
Material: PAS-60 CF10

mechanical characteristics

Characteristic	Standard	Unit	Value
Tensile strength (+23°C, dry)	ISO 527-1/-2 DIN 53455 ASTM D 638	MPa (N/mm ²)	110
Elongation at break (+23°C, dry)	ISO 527-1/-2 DIN 53455 ASTM D 638	%	4
Tensile E-modulus (+23°C, dry)	ISO 527-1/-2 DIN 53455 ASTM D 638	MPa (N/mm ²)	7000
Charpy impact strength (+23°C, dry)	ISO 179 DIN 53453	kJ/m ²	30
Charpy notched impact strength (+23°C, dry)	ISO 179 DIN 53453	kJ/m ²	3

thermal characteristics

Characteristic	Standard	Unit	Value
min. Operating temperature (continuous)		°C	-20
max. service temperature (continuous)		°C	100
max. service temperature (short-term)		°C	180

combustibility characteristics

Characteristic	Standard	Unit	Value
UL94 flammability	IEC 60695-11-10	class	HB

physical characteristics

Characteristic	Standard	Unit	Value
Density, Gross density	ISO 1183 DIN 53479 ASTM D 792	g/cm ³	1.12

These data are guideline values which are subject to change depending on the type of manufacture of the test specimens and stress. These data are based on our own experience and on manufacturer's data. However, they are provided without guarantee, since each application is different and must be considered with reference to its specific influence parameters.