

Semi-finished products faigle Industrieplast GmbH +43 5574 6811

industrieplast@faigle.com

Semi-finished products CH/LI faigle Igoplast AG +41 71 747 41 41 igoplast@faigle.com Injection moulded parts faigle Kunststoffe GmbH +43 5574 6811 kunststoffe@faigle.com

Material datasheet Material: PAS-60 V0

mechanical characteristics

Characteristic	Standard	Unit	Value
Yield strain (dry)	ISO 527-1/-2 DIN 53455 ASTM D 638	%	4
Tensile E-modulus (+23°C, dry)	ISO 527-1/-2 DIN 53455 ASTM D 638	MPa (N/mm²)	3600
Max. permissible pressure load (continuous)	Faigle	MPa (N/mm²)	13
Charpy impact strength (+23°C, dry)	ISO 179 DIN 53453	kJ/m²	75

thermal characteristics

Characteristic	Standard	Unit	Value
min. Operating temperature (continuous)		°C	-30
max. service temperature (continuous)		°C	100
max. service temperature (short-term)		°C	160
Heat deflection temperature HDT/A (1.8 N/mm²)	ISO 75-1/-2 DIN 53461 ASTM D 648	°C	70

combustibility characteristics

Characteristic	Standard	Unit	Value
UL94 flammability	IEC 60695-11-10	class	V0

electrical characteristics

Characteristic	Standard	Unit	Value
Dielectric loss factor (1 MHz, dry)	DIN IEC 60250 (DIN VDE 0303-4) ASTM D 150		0.015

These data are guideline values which are subject to change depending on the type of manufacture of the test specimens and stress. These data are based on our own experience and on manufacturer's data. However, they are provided without guarantee, since each application is different and must be considered with reference to its specific influence parameters.

14/05/24



Semi-finished products faigle Industrieplast GmbH +43 5574 6811

industrieplast@faigle.com

faigle Igoplast AG +41 71 747 41 41 igoplast@faigle.com

Semi-finished products CH/LI

Injection moulded parts faigle Kunststoffe GmbH +43 5574 6811 kunststoffe@faigle.com

physical characteristics

Characteristic	Standard	Unit	Value
Density, Gross density	ISO 1183 DIN 53479 ASTM D 792	g/cm³	1.16
Moisture absorption at saturation - standard climate (23°C, 50% RF)	ISO 62 ISO 1110	%	2.5
Water absorption at saturation (water storage 23°C)	ISO 62 DIN 53495 ASTM D 570	%	8

These data are guideline values which are subject to change depending on the type of manufacture of the test specimens and stress. These data are based on our own experience and on manufacturer's data. However, they are provided without guarantee, since each application is different and must be considered with reference to its specific influence parameters.