

Material datasheet

Material: PAS-60X

mechanical characteristics

Characteristic	Standard	Unit	Value
Tensile E-modulus (+23°C, dry)	ISO 527-1/-2 DIN 53455 ASTM D 638	MPa (N/mm ²)	2500
Max. permissible pressure load (continuous)	Faigle	MPa (N/mm ²)	11
Charpy impact strength (+23°C, dry)	ISO 179 DIN 53453	kJ/m ²	No Break
Charpy notched impact strength (+23°C, dry)	ISO 179 DIN 53453	kJ/m ²	3
Coefficient of sliding friction (p = 0.3N/mm ² / 0.6N/mm ² , v = 0.27m/s, against steel hardened and ground, dry)			0.2

thermal characteristics

Characteristic	Standard	Unit	Value
min. Operating temperature (continuous)		°C	-30
max. service temperature (continuous)		°C	80
max. service temperature (short-term)		°C	120
Coefficient of linear thermal expansion (23 - 60°C)	ISO 11359	10 ⁻⁶ /K	95

combustibility characteristics

Characteristic	Standard	Unit	Value
UL94 flammability	IEC 60695-11-10	class	HB

physical characteristics

Characteristic	Standard	Unit	Value
Density, Gross density	ISO 1183 DIN 53479 ASTM D 792	g/cm ³	1.11
Moisture absorption at saturation - standard climate (23°C, 50% RF)	ISO 62 ISO 1110	%	2.8
Water absorption at saturation (water storage 23°C)	ISO 62 DIN 53495 ASTM D 570	%	9

These data are guideline values which are subject to change depending on the type of manufacture of the test specimens and stress. These data are based on our own experience and on manufacturer's data. However, they are provided without guarantee, since each application is different and must be considered with reference to its specific influence parameters.