

Material datasheet Material: PAS-MFA

mechanical characteristics

Characteristic	Standard	Unit	Value
Yield stress (+23°C, dry)	ISO 527-1/-2 DIN 53455 ASTM D 638	MPa (N/mm ²)	11
Tensile strength (+23°C, dry)	ISO 527-1/-2 DIN 53455 ASTM D 638	MPa (N/mm ²)	28
Elongation at break (+23°C, dry)	ISO 527-1/-2 DIN 53455 ASTM D 638	%	250
Tensile E-modulus (+23°C, dry)	ISO 527-1/-2 DIN 53455 ASTM D 638	MPa (N/mm ²)	440
Max. permissible pressure load (continuous)	Faigle	MPa (N/mm ²)	3
Charpy impact strength (+23°C, dry)	ISO 179 DIN 53453	kJ/m ²	No Break

thermal characteristics

Characteristic	Standard	Unit	Value
min. Operating temperature (continuous)		°C	-190
max. service temperature (continuous)		°C	250
Coefficient of linear thermal expansion (23 - 60°C)	ISO 11359	10 ⁻⁶ /K	200

combustibility characteristics

Characteristic	Standard	Unit	Value
UL94 flammability	IEC 60695-11-10	class	V0

electrical characteristics

Characteristic	Standard	Unit	Value
Surface resistivity (dry)	DIN IEC 60093 (DIN VDE 0303-30) ASTM D 257	Ω	10 ¹⁷

These data are guideline values which are subject to change depending on the type of manufacture of the test specimens and stress. These data are based on our own experience and on manufacturer's data. However, they are provided without guarantee, since each application is different and must be considered with reference to its specific influence parameters.

physical characteristics

Characteristic	Standard	Unit	Value
Density, Gross density	ISO 1183 DIN 53479 ASTM D 792	g/cm ³	2.14
Moisture absorption at saturation - standard climate (23°C, 50% RF)	ISO 62 ISO 1110	%	0.03