

Material datasheet Material: PAS-60 FR

mechanical characteristics

| Characteristic | Standard | Unit | Value |
|----------------------------------|---|--------------------------|-------|
| Yield stress (+23°C, dry) | ISO 527-1/-2 DIN 53455 ASTM D 638 | MPa (N/mm ²) | 82 |
| Elongation at break (+23°C, dry) | ISO 527-1/-2 DIN 53455 ASTM D 638 | % | 3 |
| Tensile E-modulus (+23°C, dry) | ISO 527-1/-2 DIN 53455 ASTM D 638 | MPa (N/mm ²) | 3800 |
| Ball indentation hardness (dry) | ISO 2039-1 | MPa (N/mm ²) | 190 |

thermal characteristics

| Characteristic | Standard | Unit | Value |
|--|--|------|-------|
| min. Operating temperature (continuous) | | °C | -20 |
| max. service temperature (continuous) | | °C | 85 |
| max. service temperature (short-term) | | °C | 160 |
| Heat deflection temperature HDT/A (1.8 N/mm ²) | ISO 75-1/-2 DIN 53461 ASTM D 648 | °C | 65 |

combustibility characteristics

| Characteristic | Standard | Unit | Value |
|-------------------|-----------------|-------|-------|
| UL94 flammability | IEC 60695-11-10 | class | V0 |

electrical characteristics

| Characteristic | Standard | Unit | Value |
|---------------------------|--|------|------------------|
| Surface resistivity (dry) | DIN IEC 60093 (DIN VDE 0303-30) ASTM D 257 | Ω | 10 ¹⁶ |

These data are guideline values which are subject to change depending on the type of manufacture of the test specimens and stress. These data are based on our own experience and on manufacturer's data. However, they are provided without guarantee, since each application is different and must be considered with reference to its specific influence parameters.

physical characteristics

| Characteristic | Standard | Unit | Value |
|------------------------|-------------------------------------|-------------------|-------|
| Density, Gross density | ISO 1183 DIN 53479 ASTM D 792 | g/cm ³ | 1.17 |