

## Material datasheet

### Material: PAS-PPSU MG

#### mechanical characteristics

Characteristic	Standard	Unit	Value
Yield stress (+23°C, dry)	ISO 527-1/-2 DIN 53455 ASTM D 638	MPa (N/mm <sup>2</sup> )	77
Tensile E-modulus (+23°C, dry)	ISO 527-1/-2 DIN 53455 ASTM D 638	MPa (N/mm <sup>2</sup> )	2500
Max. permissible pressure load (continuous)	Faigle	MPa (N/mm <sup>2</sup> )	19
Charpy notched impact strength (+23°C, dry)	ISO 179 DIN 53453	kJ/m <sup>2</sup>	10
Charpy impact strength (+23°C, dry)	ISO 179 DIN 53453	kJ/m <sup>2</sup>	No Break
Coefficient of sliding friction (p = 0.3N/mm <sup>2</sup> / 0.6N/mm <sup>2</sup> , v = 0.27m/s, against steel hardened and ground, dry)			0.68

#### thermal characteristics

Characteristic	Standard	Unit	Value
min. Operating temperature (continuous)		°C	-50
max. service temperature (continuous)		°C	180
max. service temperature (short-term)		°C	210
Heat deflection temperature HDT/A (1.8 N/mm <sup>2</sup> )	ISO 75-1/-2 DIN 53461 ASTM D 648	°C	205
Coefficient of linear thermal expansion (23 - 60°C)	ISO 11359	10 <sup>-6</sup> /K	55
Thermal conductivity (+23°C)	DIN 52612	W/(m×K)	0.35

#### combustibility characteristics

Characteristic	Standard	Unit	Value
UL94 flammability	IEC 60695-11-10	class	V0

#### electrical characteristics

Characteristic	Standard	Unit	Value
Surface resistivity (dry)	DIN IEC 60093 (DIN VDE 0303-30) ASTM D 257	$\Omega$	$10^{13}$

#### physical characteristics

Characteristic	Standard	Unit	Value
Density, Gross density	ISO 1183 DIN 53479 ASTM D 792	g/cm <sup>3</sup>	1.29
Moisture absorption at saturation - standard climate (23°C, 50% RF)	ISO 62 ISO 1110	%	0.6