

Material datasheet
Material: PAS-PU 75A-TC+

mechanical characteristics

Characteristic	Standard	Unit	Value
Tensile strength (+23°C, dry)	ISO 527-1/-2 DIN 53455 ASTM D 638	MPa (N/mm ²)	31
Elongation at break (+23°C, dry)	ISO 527-1/-2 DIN 53455 ASTM D 638	%	900
Charpy notched impact strength (+23°C, dry)	ISO 179/1eA	kJ/m ²	No Break

physical characteristics

Characteristic	Standard	Unit	Value
Density, Gross density	ISO 1183 DIN 53479 ASTM D 792	g/cm ³	1.18